

AUG 16 2007

Serial No. 10/814,693

Docket No. 125686-5

**AMENDMENTS TO THE CLAIMS**

1. (Currently Amended) A method for protecting an article from a high temperature, oxidative environment, said method comprising:

providing a substrate;

coating said substrate with a metal layer, the metal layer comprising at least one metal selected from the group consisting of platinum and palladium;

providing an ion plasma deposition target, said target comprising

from about 2 atom percent to about 25 atom percent chromium, and

the balance comprising aluminum; and

depositing a protective coating onto said ~~substrate~~ metal layer using said target in an ion plasma deposition process.

2. (Original) The method of claim 1, wherein providing said target comprises providing a target further comprising a material selected from the group consisting of zirconium, hafnium, tantalum, silicon, yttrium, titanium, lanthanum, cerium, carbon, boron, and combinations thereof.

3. (Currently Amended) The method of claim 2, wherein providing said target comprises providing a target further comprising up to about 4 atom percent of a material selected from the group consisting of zirconium, hafnium, tantalum, silicon, yttrium, titanium, lanthanum, cerium, and combinations thereof; and up to about 0.2 atom percent of a material selected from the group consisting of carbon, boron, and combinations thereof.

4. (Original) The method of claim 3, wherein providing said target comprises providing a target comprising

about 9 atom percent chromium,

Serial No. 10/814,693

Docket No. 125686-5

about 1 atom percent zirconium, and

the balance comprising aluminum.

5. (Original) The method of claim 3, wherein providing said target comprises providing a target comprising

about 9 atom percent chromium,

about 1 atom percent zirconium,

about 2 atom percent tantalum, and

the balance comprising aluminum.

6. (Original) The method of claim 3, wherein providing said target comprises providing a target comprising

about 9 atom percent chromium,

about 1.5 atom percent hafnium,

about 1.5 atom percent silicon, and

at least about 85 atom percent aluminum.

7-8 (Canceled)

9. (Currently amended) The method of claim 8 1, further comprising:

heat treating said substrate after coating said substrate with said metal layer.

10. (Original) The method of claim 9, wherein heat treating comprises heating said substrate to a temperature in the range from about 900°C to about 1200°C for a time in the range from about 30 minutes to about 8 hours.

Serial No. 10/814,693

Docket No. 125686-5

11. (Original) The method of claim 7, wherein coating said substrate with a metal layer comprises coating with a layer having a thickness in the range from about 2 micrometers to about 25 micrometers.
12. (Original) The method of claim 11, wherein coating said substrate with a metal layer comprises coating with a layer having a thickness in the range from about 2 micrometers to about 6 micrometers.
13. (Original) The method of claim 1, further comprising heat treating said substrate after depositing said protective coating.
14. (Original) The method of claim 13, wherein heat treating comprises heating said substrate to a temperature in the range from about 700°C to about 1200°C for a time in the range from about 30 minutes to about 8 hours.
15. (Original) The method of claim 1, wherein providing said substrate comprises providing at least one of a nickel alloy, an iron alloy, and a cobalt alloy.
16. (Original) The method of claim 15, wherein providing said substrate comprises providing a superalloy.
17. (Original) The method of claim 16, wherein providing said superalloy comprises providing a component for service in a hot gas path of a gas turbine assembly.
18. (Original) The method of claim 1, wherein providing a substrate comprises providing a substrate comprising at least one coating.
19. (Original) The method of claim 1, wherein providing said ion plasma deposition target comprises providing a target manufactured using at least one of casting and powder metallurgy processing.
20. (Original) The method of claim 1, wherein depositing said protective coating onto said substrate further comprises applying a negative potential bias to said substrate.

Serial No. 10/814,693

Docket No. 125686-5

21. (Original) The method of claim 20, wherein applying said negative potential bias comprises applying a potential bias in the range from about -10 volts to about -1000 volts.

22. (Original) The method of claim 21, wherein applying said negative potential bias comprises applying a potential bias in the range from about -50 volts to about -250 volts.

23. (Original) The method of claim 1, wherein depositing said protective coating onto said substrate further comprises grounding said substrate.

24. (Original) The method of claim 1, wherein depositing said protective coating comprises depositing a protective coating having a thickness in the range from about 5 micrometers to about 250 micrometers.

25. (Original) The method of claim 24, wherein depositing said protective coating comprises depositing a protective coating having a thickness in the range from about 25 micrometers to about 75 micrometers.

26. (Original) The method of claim 1, further comprising coating said protective layer with a thermal barrier coating.

27. (Original) The method of claim 26, wherein coating said protective layer with a thermal barrier coating comprises coating said protective layer with a thermal barrier coating comprising yttria-stabilized zirconia.

28. (Original) The method of claim 1, wherein depositing said protective coating comprises forming a protective coating comprising at least 80 volume percent of a single phase.

29. (Original) The method of claim 28, wherein depositing said protective coating comprises forming a protective coating comprising at least 80 volume percent of a B2-structured aluminide intermetallic phase.

Serial No. 10/814,693

Docket No. 125686-5

30. (Original) The method of claim 1, wherein depositing said protective coating comprises forming a protective coating comprising at least two phases.

31. (Original) The method of claim 30, wherein depositing said protective coating comprises forming a protective coating comprising a B2-structured aluminide intermetallic phase and platinum aluminide (PtAl<sub>2</sub>).

32. (Currently Amended) A method for protecting an article from a high temperature, oxidative environment, said method comprising:

providing a substrate comprising a nickel-based superalloy;

coating said substrate with a metal layer, the metal layer comprising at least one metal selected from the group consisting of platinum and palladium;

heat treating said substrate after coating said substrate with said metal layer;

providing an ion plasma deposition target, said target comprising

from about 2 atom percent to about 25 atom percent chromium,

up to about 4 atom percent of a material selected from the group consisting of zirconium, hafnium, tantalum, silicon, yttrium, titanium, lanthanum, cerium, and combinations thereof,

up to about 0.2 percent of a material selected from the group consisting of carbon, boron, and combinations thereof, and

at least about 70 atom percent aluminum;

depositing a protective coating onto said ~~substrate~~ metal layer using said target in an ion plasma deposition process, wherein a negative potential bias is applied to said substrate during deposition of said protective coating; and

heat treating said substrate after depositing said protective coating;

Serial No. 10/814,693

Docket No. 125686-5

wherein after heat treating, said protective coating comprises a B2-structured aluminide intermetallic phase.

33-41 (Canceled)